



Elastic and Piezoelectric Properties of Boron Nitride Nanotube Composites

I: Molecular Dynamics of a Single Wall BNNT

V. I. Yamakov, J. H. Kang
National Institute of Aerospace
Hampton, VA

C. Park, K. Wise, C. Fay
NASA Langley Research Center
Hampton, VA

A. H. Kim
University of Bath, Bath, UK

International Symposium on Piezocomposite Applications - ISPA 2015





Outline

- Background and motivation
- Piezoelectric molecular dynamics model of boron nitride nanotubes (BNNTs)
- Analytical and simulation results
- Summary





Nanotube Comparison

	Carbon Nanotubes 	Boron Nitride Nanotubes 
Mechanical Properties (Axial Young's Modulus)	1.33 TPa (very stiff)	1.18 TPa (very stiff)
Axial Thermal Conductivity	>3000 W/mK (highly conductive)	~300–3000 W/mK (highly conductive)
Axial Coefficient of Thermal Expansion	$\sim 1 \times 10^{-6} \text{ K}^{-1}$ (very low)	$\sim 1 \times 10^{-6} \text{ K}^{-1}$ (very low)
Electric Properties	Metallic or semiconducting	Insulator (6.0 eV band gap, 10^{15-18} ohm-cm) Dielectric strength $2 \times 10^5 \text{ V/mm}$ Piezoelectric ($0.25\text{-}0.4 \text{ C/m}^2$)
Thermal Oxidation Resistance	Stable up to 300-400 °C in air	Stable to over 800 °C in air
Neutron Absorption Cross-Section	C = 0.0035 barn	B = 767 barn ($B^{10} \sim 3800 \text{ barn}$) N = 1.9 barn (Excellent neutron radiation shielding)
Color	Black	White (can be dyed to color)



Langley All-Nanotubes Actuator/Sensor Film



Goal: flexible, mechanically durable, large actuation, high sensitivity
Modeling is essential in achieving these goals




Molecular Dynamics Model of BNNTs

- Define forces between atoms using a given interatomic potential (energy)

$$U_r = \sum_{i,j} [V_R(r_{ij}) - B_{ij}V_A(r_{ij})]; \quad \vec{F}_i = -\partial U_r / \partial \vec{r}_i$$

- Evolve atoms according to Newton's law: $\vec{a}_i = \vec{F}_i / m_i$



Tersoff – Brenner type of potential:

- Albe et al., (Rad. Eff. Def. Sol. 141 (1997) 85)
- Verma – Sekkal: (Nanotechnology 18 (2007) 435711)

Total potential energy:

$$U_r = \frac{1}{2} \sum_{i,j \neq i} V_R(r_{ij}) - B_{ij}V_A(r_{ij}) = \sum_i U_i$$

where:

$$V_R(r_{ij}) = F_c(r_{ij}) \frac{D_0}{S-1} \exp(-\beta \sqrt{2S}(r_{ij} - r_0)) \quad \text{- repulsive term}$$

$$V_A(r_{ij}) = F_c(r_{ij}) \frac{SD_0}{S-1} \exp(-\beta \sqrt{2/S}(r_{ij} - r_0)) \quad \text{- attractive term}$$

$$F_c(r_{ij}) = \begin{cases} 1 & r \leq R_1 \\ 0.5 \left[1 + \cos \left(\pi \frac{r_{ij} - R_1}{R_2 - R_1} \right) \right] & R_1 < r_{ij} \leq R_2 \\ 0 & R_2 < r_{ij} \end{cases} \quad \text{- cut-off function}$$

$$B_{ij} = (1 + \gamma^n P_{ij}^n)^{-\frac{1}{2n}}$$

$$P_{ij} = \sum_{k \neq i,j} F_c(r_{ik}) G(\theta_{ijk}) \exp[\lambda^3 (r_{ij} - r_{ik})^3]$$

$$G(\theta_{ijk}) = 1 + \frac{c_0^2}{d_0^2} - \frac{c_0^2}{d_0^2 + (h_0 - \cos \theta_{ijk})^2} \quad \text{- angular dependent 3-body term}$$


θ_{ijk} is the angle between bonds $i-j$ and $i-k$.

MD models do not currently address the piezoelectric behavior



Piezoelectric Properties of BNNTs

Piezoelectric Effect



(Sai & Mele, PRB 68, (2003) 241405)

Induced polarization, \vec{p} , under strain ϵ_{jk} : $p_i = e_{ijk} \epsilon_{jk}$

where e_{ijk} - piezoelectric tensor with symmetry:

$$e_{xxx} = -e_{xyy} = -e_{yyx} = -e_{yxy}; \quad e_{xxx} = 0.086 - 0.12 \text{ e / Bohr}$$

The MD model has to reproduce the characteristic polarization behavior



MD Model for a Piezoelectric BNNT


Introduce a dipole term to the interatomic potential

$$U = U_r + U_p; \quad U_p = \sum_{i=\{B\}, j=\{N\}} U(\vec{p}_{BN,ij})$$


Dipole Parametric Equation:

$$\vec{p}_{BN,ij} = p_0 \left[\frac{r_{BN,ij} - r_0}{r_0} + t_\theta \sum_{k=1}^4 \left(\frac{1}{2} + \cos \theta_k \right) \right]$$

p_0, t_θ - fitting parameters



The dipole term is simple, efficient, and allows for analytic expression of the piezoelectric tensor



Analytical Model for a Piezoelectric BNNT

Shell Theory of the Hexagonal BN Lattice*

During homogeneous deformation the h-BN lattice sustains force equilibrium by shifting the N-sublattice at a shift vector ζ with respect to the B-sublattice.

ζ is determined by the equilibrium condition:


$$\partial\Phi/\partial\zeta_\lambda = 0 \quad \text{with}$$

$$\Phi = \sum_{j=1}^3 V(r_{ij}; \cos\theta_{ijk}, k \neq i, j) \quad \text{and}$$

$$V(r_{ij}; \cos\theta_{ijk}) = V_R(r_{ij}) - B_{ij}V_A(r_{ij})$$

as a function of the interatomic potential parameters:

Shift between B and N sub-lattices



$$\zeta_\lambda = \frac{2}{3} A \varepsilon_{\alpha\beta} \sum_{j=1}^3 n_\alpha^j n_\beta^j n_\lambda^j \quad \text{with} \quad A = 1 - \frac{8r_0^2 \left(\frac{\partial^2 V}{\partial r_{ij}^2} \right)_0 + 12r_0 \left(\frac{\partial^2 V}{\partial r_{ij} \partial \cos\theta_{ijk}} \right)_0}{4r_0^2 \left(\frac{\partial^2 V}{\partial r_{ij}^2} \right)_0 + 12r_0 \left(\frac{\partial^2 V}{\partial r_{ij} \partial \cos\theta_{ijk}} \right)_0 + 18 \left(\frac{\partial^2 V}{\partial \cos\theta_{ijk} \partial \cos\theta_{ijk}} \right)_0 - 9 \left(\frac{\partial^2 V}{\partial \cos\theta_{ijk} \partial \cos\theta_{ijl}} \right)_0 + 12 \left(\frac{\partial V}{\partial \cos\theta_{ijk}} \right)_0}$$

and for r_{ij} and $\cos\theta_{ijk}$:

$$r_{ij}^2 = r_0^2 (\delta_{\alpha\beta} + 2\varepsilon_{\alpha\beta}) (n_\alpha + \zeta_\alpha) (n_\beta + \zeta_\beta) - r_0^4 [k_{\alpha\beta} (n_\alpha + \zeta_\alpha) (n_\beta + \zeta_\beta)]^2 / 12$$

$$\cos\theta_{ijk} = \frac{r_0^2}{r_{ij} r_{ik}} (n_\alpha^{ij} + \zeta_\alpha) (n_\lambda^{ik} + \zeta_\lambda) \times \left\{ \delta_{\alpha\lambda} + 2\varepsilon_{\alpha\lambda} + \frac{r_0^2}{12} k_{\alpha\beta} k_{\gamma\lambda} [3(n_\beta^{ij} + \zeta_\beta) (n_\gamma^{ik} + \zeta_\gamma) - 2(n_\beta^{ij} + \zeta_\beta) (n_\gamma^{ij} + \zeta_\gamma) - 2(n_\beta^{ik} + \zeta_\beta) (n_\gamma^{ik} + \zeta_\gamma)] \right\}$$




Expressing Polarization*

Parametric equation:
$$\vec{p}_{BN,ij} = p_0 \left[\frac{r_{BN,ij} - r_0}{r_0} + t_\theta \sum_{k=1}^4 \left(\frac{1}{2} + \cos \theta_k \right) \right]$$

Substituting r_{ij} , and $\cos \theta_{ijk}$, and limiting to linear terms of $\varepsilon_{\alpha\beta}$, and $r_0^2 \kappa_{\alpha\beta}^2$, excluding rotation, $\varepsilon_{xy} = \varepsilon_{yx}$:

$$\begin{cases} \vec{p}_{cell,x} = \frac{p_0}{2\sqrt{3}r_0^2} \left\{ (1+A)(\varepsilon_{xx} - \varepsilon_{yy}) - \frac{r_0^2}{96}(5k_{xx}^2 - 2k_{xx}k_{yy} - 3k_{yy}^2) - \right. \\ \left. -t_\theta \left[3(1-A)(\varepsilon_{xx} - \varepsilon_{yy}) - \frac{r_0^2}{96}(23k_{xx}^2 + 42k_{xx}k_{yy} - 81k_{yy}^2) \right] \right\} \\ \vec{p}_{cell,y} = -\frac{p_0}{2\sqrt{3}r_0^2} [(1+A) - 3t_\theta(1-A)] \varepsilon_{xy} \end{cases}$$

General equation expressing polarization of any deformed h-BN layer through the interatomic potential (A and r_0), and two fitting parameters, p_0 and t_θ .





Polarization of a hexagonal BN Plane

In plane deformation: $\kappa_{\alpha\beta} = 0$

$$\begin{aligned} p_x &= \frac{P_0}{2\sqrt{3}r_0^2} [(1+A) - 3t_\theta(1-A)] \epsilon_{xx} - \frac{P_0}{2\sqrt{3}r_0^2} [(1+A) - 3t_\theta(1-A)] \epsilon_{yy} \\ p_y &= -\frac{P_0}{2\sqrt{3}r_0^2} [(1+A) - 3t_\theta(1-A)] \epsilon_{xy} \end{aligned}$$

Piezoelectric tensor:

$$p_x = e_{xxx} \epsilon_{xx} + e_{xyy} \epsilon_{yy}$$


$$p_y = e_{yxy} \epsilon_{xy} = e_{yyx} \epsilon_{yx}$$

$$e_{xxx} = -e_{xyy} = -e_{yxy} = -e_{yyx} = \frac{P_0}{2\sqrt{3}r_0^2} [(1+A) - 3t_\theta(1-A)]$$


Preserves the hexagonal symmetry

Model Parameters

	U_r			p		
	r_0 (nm)	A	E (TPa)	p_0 (e/nm)	t_θ	e_{xxx} (e/Bohr)
Albe et al.	0.1462	0.276	1.11	0.029	-1.4	0.0894
Verma-Sekkal	0.1457	0.241	1.48	0.041	-0.75	0.0870



Stretched h-BN Plane




* N. Sai, E.J. Mele, PRB 68 (2003) 241405




Polarization of a BNNT

Zig-zag (n 0) tube: $\kappa_{xx} = 0$; $\kappa_{yy} = 1/R$; $r_0^2 / R^2 \ll 1$

Folded along x-axis



$$R = nr_0 \sqrt{3}/2\pi$$



MD simulation of a BNNT under stretch

$$p = p_x = \frac{P_0}{2\sqrt{3}r_0^2} \left[(1+A) - 3t_\theta(1-A) \right] (1+\nu) \epsilon_{xx} + \underbrace{\frac{P_0}{64\sqrt{3}R^2} (1-27t_\theta)}_{\text{Spontaneous polarization}} \quad (1)$$


Valid in the limit $r_0^2 \kappa_{yy}^2 = r_0^2 / R^2 \ll 1$

No polarization in twist, ϵ_{xy}

Spontaneous polarization $\sim 1/R^2$

$$p_{sp} = \text{const} / R^2$$

MD Results






Polarization of a BNNT

Armchair tube: (n n) $\kappa_{xx} = 1/R$; $\kappa_{yy} = 0$; $r_0^2 / R^2 \ll 1$

Folded along y-axis





$$p = p_y = -\frac{P_o}{2\sqrt{3}r_0^2}[(1+A)-3t_\theta(1-A)]\varepsilon_{xy}$$

No polarization in stretch, ε_{yy}
No spontaneous polarization

MD Results

Piezoelectric Polarization in Twist



MD simulation of a BNNT under twist



Polarization of a BN Nanotube


Chiral tube $(n\ m)$ with chiral angle, $\tan\varphi = \frac{m\sqrt{3}}{m+2n}$:

Folded at angle φ

$$p_x = e_{11}\epsilon_s + e_{14}\epsilon_t$$


$$e_{11} = \frac{p_o \cos 3\varphi}{2\sqrt{3}r_0^2} [(1+A) - 3t_\theta(1-A)](1+\nu)$$

$$e_{14} = -\frac{p_o \sin 3\varphi}{2\sqrt{3}r_0^2} [(1+A) - 3t_\theta(1-A)]$$




MD Results

Polarization in Stretch



Polarization in Twist





Summary

Parametric equation: $\vec{p}_{BN,ij} = p_0 \left[\frac{r_{BN,ij} - r_0}{r_0} + t_\theta \sum_{k=1}^4 \left(\frac{1}{2} + \cos \theta_k \right) \right]$

- Analytic expression of the piezoelectric coefficients through the interatomic potential

$$e_{xxx} = -e_{xyy} = -e_{yxy} = -e_{yyx} = \frac{p_0}{2\sqrt{3}r_0^2} [(1+A) - 3t_\theta(1-A)]$$

- The model reproduces the piezoelectric properties predicted by first-principle
- The model predicts $1/R^2$ spontaneous polarization of BNNTs

Limitations of the analytical model:

- Valid for small curvature (bending): tubes with $r_0^2/R^2 \ll 1$, or $R > 1$ nm (most experimental BNNTs)

Acknowledgments

- NASA – NIA cooperative agreement NNL09AA00A
- US Air Force Office of Scientific Research - Low Density Materials program: Grant No. FA9550-11-1-0042
- NASA Langley Research Center IRAD program